

# COMPATIBILITY CHART

## LEGEND

- A - RECOMMENDED
- B - MINOR TO MODERATE EFFECT
- C - MODERATE TO SEVERE
- U - UNSATISFACTORY
- BLANK - INSUFFICIENT DATA

## Chemical

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polyulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Acetaldehyde	U	A	B	B	U	U	C	B	U	U	U	U	U
Acetamide	U	A	B	B	U	U	C	B	U	U	U	U	U
Acetic Acid 5%	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetic Acid 30%	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetic Acid, Hot High Press	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetic Acid, Glacia	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetic Anhydride	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetone	B	B	B	B	U	U	A	B	U	U	U	U	U
Acetophenone	B	B	B	B	U	U	A	B	U	U	U	U	U
Acetyl Acetone	B	B	B	B	U	U	A	A	U	U	U	U	U
Acetyl Chloride	B	B	B	B	U	U	A	B	U	U	U	U	U
Acetylene	B	B	B	B	U	U	A	B	U	U	U	U	U
Acetylene Tetrabomide	B	B	B	B	U	U	A	B	U	U	U	U	U
Acrylonitrile	B	B	B	B	U	U	A	B	U	U	U	U	U
Adipic Acid	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Lubriplate	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Safe 2300	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Safe 2300W	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Shell IAC	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Shell 7A Grease	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Shell 17 Grease	B	B	B	B	U	U	A	B	U	U	U	U	U
Aero Shell 750	B	B	B	B	U	U	A	B	U	U	U	U	U
Aerozene 50 (50% Hydrazine UDMH)	B	B	B	B	U	U	A	B	U	U	U	U	U
Air-Below 300 F	B	B	B	B	U	U	A	B	U	U	U	U	U
Air-Above 300 F	B	B	B	B	U	U	A	B	U	U	U	U	U
Alkazene	B	B	B	B	U	U	A	B	U	U	U	U	U
Alum-NH <sub>3</sub> Cr-K	A	A	A	A	U	U	A	A	U	U	U	U	U
Aluminum Acetat	A	A	B	A	U	U	A	B	U	U	U	U	U
Aluminum Bromide	A	A	A	A	U	U	A	B	U	U	U	U	U
Aluminum Chloride	A	A	A	A	U	U	A	B	U	U	U	U	U
Aluminum Fluoride	B	A	A	A	U	U	A	B	U	U	U	U	U
Aluminum Nitrate	A	A	A	A	U	U	A	A	U	U	U	U	U
Aluminum Phosphate	A	A	A	A	U	U	A	A	U	U	U	U	U
Aluminum Salts	A	A	A	A	U	U	A	A	U	U	U	U	U
Aluminum Sulfate	A	A	B	A	U	U	A	A	U	U	U	U	U
Ambrex 33 Mobil	U	U	U	U	U	U	A	B	C	B	U	C	U
Amines,Mixed	B	B	B	B	U	U	B	B	U	U	B	U	U
Ammonia Anhydrous(Liquid)	U	U	U	A	A	B	B	A	U	U	C	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Ammonia Gas,Cold	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonia Gas,Hot	U	U	B	B	U	B	B	B	U	U	U	U	U
Ammonia and Lithium Metalin Solution	U	U	B	B	U	B	B	B	U	U	U	U	U
Ammonium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Hydroxide(Concentrated)	U	U	A	A	U	A	A	A	U	U	U	U	U
Ammonium Nitrate	C	A	A	A	A	A	A	A	A	A	A	B	B
Ammonium Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Persulfate Solution	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Persulfate 10%	A	U	A	A	A	U	A	A	U	U	U	U	U
Ammonium Phosphate	B	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Phosphate, Mono-Basic	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Phosphate, Dibasic	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Phosphate, Tribasic	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Salts	A	A	A	A	A	A	A	A	A	A	A	C	C
Ammonium Sulfate	A	B	A	A	A	A	A	A	A	U	U	A	A
Ammonium Sulfide	A	B	A	A	A	A	A	A	A	U	U	U	U
Amyl Acetate	U	U	A	A	A	U	U	U	U	U	U	U	U
Amyl Alcohol	B	B	A	A	A	B	A	A	A	B	U	U	A
Amyl Borate	U	U	U	U	U	U	U	U	U	U	A	U	A
Amyl Chloride	U	U	U	U	U	U	U	U	U	U	U	B	A
Amyl Chloranaphthalene	U	U	U	U	U	U	U	U	U	U	U	B	A
Amyl Naphthalene	U	U	U	U	U	U	U	U	U	U	U	U	A
Anderol L-774 (di-ester)	U	U	U	U	U	U	U	U	B	U	U	U	A
Anderol L-826 (di-ester)	U	U	U	U	U	U	U	U	B	U	U	U	A
Anderol L-829 (di-ester)	U	U	U	U	U	U	U	U	B	U	U	U	A
Ang-25 (Glyceral Ester)	B	B	B	A	A	B	B	B	B	B	B	B	B
Ang-25 (Di-ester Base) (TG749)	U	U	B	U	U	B	B	B	U	U	B	B	B
Anhydrous Ammonia	U	U	U	A	A	B	B	A	A	U	U	U	A
Anhydrous Hydrazine	U	U	U	A	B	B	B	B	B	B	U	U	U
Anhydrous Hydrogen Fluoride	U	U	U	A	B	A	B	U	U	U	U	U	C
Aniline	U	U	U	B	B	B	B	U	U	U	U	U	C
Aniline Dyes	B	B	B	B	B	B	B	B	B	B	B	B	B
Aniline Hydrochloride	B	C	B	B	B	B	B	B	B	B	B	B	B
Aniline Oils	U	U	B	B	B	B	B	U	U	U	U	B	C
Animal Fats	U	U	B	B	B	B	A	B	B	B	B	B	A
Animal Oils	U	U	B	B	B	B	A	B	B	B	B	B	A
AN-O-3 Grade M	U	U	B	U	U	U	A	B	B	B	B	A	A
AN-O-6	U	U	U	U	U	U	U	B	B	B	B	A	A
AN-O-366	U	U	U	U	U	U	A	B	B	B	B	A	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
AN-VV-O-366b Hdry. Fluid	A	C	B	B	B	B	B	B	B	B	B	B	A
Ansul Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Aqua Regia	U	U	U	U	U	U	U	U	U	U	U	U	U
Argon	U	U	U	U	U	U	U	U	U	U	U	U	U
Aroclor 1248	U	U	U	U	U	U	U	U	U	U	U	U	U
Aroclor 1254	U	U	U	U	U	U	U	U	U	U	U	U	U
Aroclor 1260	U	U	U	U	U	U	U	U	U	U	U	U	U
Aromatic Fuel 50%	U	U	U	U	U	U	U	U	U	U	U	U	U
Arsenic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Arsenic Trichloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Askarel	U	U	U	U	U	U	U	U	U	U	U	U	U
Asphalt	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Oil #1	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Oil #2	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Oil #3	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Oil #4	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Reference Fuel A	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Reference Fuel B	U	U	U	U	U	U	U	U	U	U	U	U	U
ASTM Reference Fuel C	U	U	U	U	U	U	U	U	U	U	U	U	U
ATL-857	U	U	U	U	U	U	U	U	U	U	U	U	U
Atlantic Dominion F	U	U	U	U	U	U	U	U	U	U	U	U	U
Aurex 903R Mobil	U	U	U	U	U	U	U	U	U	U	U	U	U
Automatic Transmission Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Automotive Brake Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
B	U	U	U	U	U	U	U	U	U	U	U	U	U
Bardol B	U	U	U	U	U	U	U	U	U	U	U	U	U
Barium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Salts	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Sulfide	A	A	B	A	A	A	A	A	A	A	A	A	A
Bayol D	U	U	U	U	U	U	U	U	U	U	U	U	U
Beer	A	A	A	A	A	A	A	A	A	A	A	A	A
Beer Sugar Liquors	A	A	A	A	A	A	A	A	A	A	A	A	A
Benzaldehyde	U	U	U	U	U	U	U	U	U	U	U	U	U
Benzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Benzenesulfonic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Benzine	U	U	U	U	U	U	U	U	U	U	U	U	U
Benzochloride	U	U	U	U	B	A	U	U	U	U	U	U	U
Benzoic Acid	U	U	U	U	U	U	U	U	U	U	U	B	B

**LEGEND**
**A - RECOMMENDED**
**B - MINOR TO MODERATE EFFECT**
**C - MODERATE TO SEVERE**
**U - UNSATISFACTORY**
**BLANK - INSUFFICIENT DATA**
**Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Benzophenone													
Benzyl Alcohol													
Benzyl Benzoate													
Benzyl Chloride													
Black Point 77													
Black Sulphate Liquors													
Black Furnace Gas													
Bleach Solutions													
Borax													
Bordeaux Mixture													
Boric Acid													
Boron Fluids(HEF)													
Brake Fluid(Non-Petroleum)													
Bray GG-130													
Brayco 719-R (VV-H-910)													
Brayco 885 (MIL-L-6085A)													
Brayco 910													
Brett 710													
Brine													
Brom-113													
Brom-114													
Bromine													
Bromine Anhydrous													
Bromine Pentafluoride													
Bromine Trifluoride													
Bromine Water													
Bromobenzene													
Bromochloro Trifluoroethane													
Bunker Oil													
Butadiene													
Butane													
Butane 2,2-Dimethyl													
Butane 2,3-Dimethyl													
Butanol (Butyl Alcohol)													
1-Butene,2-Ethyl													
Butter													
Butyl Acetate													
Butyl Acetyl Ricinoleate													
Butyl Acrylate													
Butyl Alcohol													

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Butyl Amine	U	A	A	U	U	U	U	U	U	U	U	U	U
Butyl Benzoate	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Butyrate	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Carbitol	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Cellosolve	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Cellosolve Adipate	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Oleate	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyl Stearate	U	U	U	U	U	U	U	U	U	U	U	U	U
Butylene	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyraldehyde	U	U	U	U	U	U	U	U	U	U	U	U	U
Butyric	U	U	U	U	U	U	U	U	U	U	U	U	U
C													
Calcine Liquors													
Calcium Acetate	A	U	A	A	A	B	B	B	B	B	U	U	A
Calcium Bisulfite	U	U	U	U	U	A	A	A	A	A	U	A	A
Calcium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Hypochloride	U	U	U	A	A	U	B	B	B	U	U	A	A
Calcium Hypochlorite	U	U	U	A	A	C	B	C	A	U	U	B	B
Calcium Nitrate	A	A	A	A	A	A	A	A	A	A	A	B	A
Calcium Phosphate	A	A	A	A	A	A	A	B	B	A	A	B	A
Calcium Salts	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Silicate	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Sulfide	B	B	A	A	A	B	B	B	A	A	U	B	A
Calcium Sulfite	B	B	A	A	A	B	A	A	A	A	B	A	A
Calcium Thiosulfate	B	B	A	A	A	B	A	A	A	A	B	A	A
Caliche Liquors	A	A	A	A	A	A	A	A	A	A	A	B	A
Cane Sugar Liquors	A	A	A	A	A	A	A	A	A	A	U	A	A
Caproic Aldehyde	B		B	B	B	C	B	B	B	B	B	B	U
Carbamate	U	U	B	B	B	C	B	B	B	B	B	B	A
Carbitol	B	B	B	B	B	B	B	B	B	B	B	B	B
Carboxylic Acid	U	U	B	B	B	U	C	C	C	C	U	B	A
Carbon Bisulfide													
Carbon Dioxide, Dry	B	B	B	B	B	A	A	B	B	B	B	B	B
Carbon Dioxide, Wet	B	B	B	B	B	A	B	B	B	B	B	B	B
Carbon Disulfide	U	U	B	U	U	U	U	U	U	U	U	A	A
Carbon Monoxide	B	B	A	A	A	A	A	A	A	A	U	B	B

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Carbon Tetrachloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Carbonic Acid	A	A	A	A	A	A	A	A	A	A	A	A	A
Castor Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellosolve	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellosolve Acetate	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellosolve Butyl	U	U	U	U	U	U	U	U	U	U	U	U	U
Celluguard	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellulube A60 Now Fyrquel	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellulube90,100,150,220,300,500	U	U	U	U	U	U	U	U	U	U	U	U	U
Cellutherm 2505A	U	U	U	U	U	U	U	U	U	U	U	U	U
Cetane (Hexadecane)	U	U	U	U	U	U	U	U	U	U	U	U	U
China Wod Oil (Tung Oil)	U	U	U	U	U	U	U	U	U	U	U	U	U
Chloracetic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorodane	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorestol	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorinated Salt Brine	B	U	U	U	U	U	U	U	U	U	U	U	U
Chlorinated Solvents, Dry	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorinated Solvents, Wet	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorine,Dry	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorine, Wet	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorine Dioxide	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorine Dioxide(8% Cl as NaClO <sub>2</sub> in solutio	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorine Trifluoride	U	U	U	U	U	U	U	U	U	U	U	U	U
Chloroacetone	U	U	U	U	U	U	U	U	U	U	U	U	U
Chloroacetic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorobenzene, (Mono)	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorobromo Methane	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorobutadiene	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorododecane	U	U	U	U	U	U	U	U	U	U	U	U	U
Chloroform	U	U	U	U	U	U	U	U	U	U	U	U	U
O-Chloronaphthalene	U	U	U	U	U	U	U	U	U	U	U	U	U
1-Chloro 1-Nitro Ethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorosulfonic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorotoluene	U	U	U	U	U	U	U	U	U	U	U	U	U
Chlorox	U	U	U	U	U	U	U	U	U	U	U	U	U
O-Chlorophenol	U	U	U	U	U	U	U	U	U	U	U	U	U
Chrome Alum	A	A	A	A	A	A	A	A	A	A	A	A	A
Chrome Plating Solutions	U	U	U	U	U	U	U	U	U	U	U	U	U
Chromic Acid	U	U	U	C	C	U	U	U	U	U	B	C	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Chromic Oxide .88 Wt.% Aqueous Solution	B	B	B	B	A	A	B	B	B	B	B	B	B
Circo Light Process Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Citric Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
City Service Koolmotor-AP Gear Oil 140-E.P.I	U	U	U	U	U	U	U	U	U	U	U	U	U
City Service Pacemaker #2	U	U	U	U	U	U	U	U	U	U	U	U	U
City Service #65,#120,#250	U	U	U	U	U	U	U	U	U	U	U	U	U
Cobalt Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Cobalt Chloride,2N	U	U	U	U	U	U	U	U	U	U	U	U	U
Cocoanut Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Cod Liver Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Coffee	U	U	U	U	U	U	U	U	U	U	U	U	U
Coke Oven Gas	U	U	U	U	U	U	U	U	U	U	U	U	U
Coliche Liquors	U	U	U	U	U	U	U	U	U	U	U	U	U
Convelex 10	U	U	U	U	U	U	U	U	U	U	U	U	U
Coolanol (Monsanto)	U	U	U	U	U	U	U	U	U	U	U	U	U
Coolanol 45 (Monsanto)	U	U	U	U	U	U	U	U	U	U	U	U	U
Copper Acetate	A	U	U	A	A	A	A	A	A	A	A	A	A
Copper Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Copper Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A
Copper Salts	A	A	A	A	A	A	A	A	A	A	A	A	A
Copper Sulfate	B	B	B	A	A	A	A	A	A	A	A	A	A
Copper Sulfate 10%	B	B	B	A	A	A	A	A	A	A	A	A	A
Copper Sulfate 50%	A	B	B	A	A	A	A	A	A	A	C	A	A
Corn Oil	U	U	U	C	C	C	A	A	C	B	A	A	A
Cottonseed Oil	U	U	U	C	C	C	A	A	C	B	A	A	A
Creosols	U	U	U	U	U	U	U	U	U	U	U	U	U
Creosote	U	U	U	U	U	U	U	U	U	U	U	U	U
Creosote, Cooler Tar	U	U	U	U	U	U	U	U	U	U	U	U	U
Creosote,Wood	U	U	U	U	U	U	U	U	U	U	U	U	U
Creosolic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Crude Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Cumene	U	U	U	U	U	U	U	U	U	U	U	U	U
Cutting Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Cyclohexane	U	U	U	U	U	U	U	U	U	U	U	U	U
Cyclohexanol	U	U	U	U	U	U	U	U	U	U	U	U	U
Cyclohexanone	U	U	U	B	U	B	U	U	U	U	U	U	U
P-Cymene	U	U	U	B	U	B	U	U	U	U	U	U	U
D													
Decalin	U	U	U	U	U	U	U	U	U	U	B	U	A
Decane	U	U	U	U	U	U	U	U	B	U	B	A	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<b>Fluoro Elastomers</b>	<b>Fluorosilicone</b>	<b>Silicone</b>	<b>Polysulfide</b>	<b>Urethane, Polyurethane</b>	<b>Hypalon</b>	<b>Neoprene</b>	<b>Hydrin</b>	<b>Buna-N, Nitrile, NBR</b>	<b>EPR, EPT, EPDM</b>	<b>Butyl</b>	<b>SBR, GRS</b>	<b>Natural Rubber</b>
Delco Brake Fluid	U	A	A	C	U	B	B	B	A	U	U	U	U
Denatured Alcohol	A	A	A	A	A	A	B	A	A	A	A	A	A
Detergent Solutions	B	B	A	A	A	B	B	B	B	B	B	B	B
Developing Fluids (Photo)	A	B	B	B	B	U	B	U	U	U	U	U	U
Dextron	U	U	U	U	U	U	U	U	U	U	U	U	U
Diacetone	U	U	U	U	U	U	U	U	U	U	U	U	U
Diacetone Alcohol	U	U	U	U	U	U	U	U	U	U	U	U	U
Diazinon	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibenzyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibenzyl Sebacate	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibromoethyl Benzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibutylamine	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibutyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibutyl Phthalate	U	U	U	U	U	U	U	U	U	U	U	U	U
Dibutyl Sebacate	U	U	U	U	U	U	U	U	U	U	U	U	U
O-Dichlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
P-Dichlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Dichloro-Butane	U	U	U	U	U	U	U	U	U	U	U	U	U
Dichloro-Isopropyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Dicyclohexylamine	U	U	U	U	U	U	U	U	U	U	U	U	U
Diesel Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Di-ester Lubricant MIL-L-7808	U	U	U	U	U	U	U	U	U	U	U	U	U
Di-ester Synthetic Lubricants	U	U	U	U	U	U	U	U	U	U	U	U	U
Diethylamine	B	B	B	B	B	B	B	B	B	B	B	B	B
Diethyl Benzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Diethyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Diethyl Sebacate	U	U	U	U	U	U	U	U	U	U	U	U	U
Diethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A
Difluorodibromomethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Diisobutylene	U	U	U	U	U	U	U	U	U	U	U	U	U
Diisoctyl Sebacate	U	U	U	U	U	U	U	U	U	U	U	U	U
Diisopropyl Benzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Diisopropyl Ketone	U	U	U	A	A	A	A	U	U	U	U	U	U
Dimethyl Aniline	U	U	U	U	U	B	B	B	B	B	B	B	B
Dimethyl Formamide	U	U	U	U	U	B	B	B	B	B	B	B	B
Dinitro Toluene	U	U	U	U	U	B	B	B	B	B	B	B	B
Diocyl Phthalate	U	U	U	B	B	B	B	B	B	B	B	B	B
Diocyl Sebacate	U	U	U	B	B	B	B	B	B	B	B	B	B
Dioxane	U	U	U	B	B	B	B	B	B	B	B	B	B
Dioxolane	U	U	U	C	B	B	B	B	B	B	B	B	B

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Dipentene	U	U	U	U	U	U	U	U	U	U	U	U	U
Diphenyl	U	U	U	U	U	U	U	U	U	U	U	U	U
Diphenyl Oxides	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Chemical 50-4	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Chemical ET378	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Chemical ET588	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-3	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-4	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-5	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-11	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-33	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-44	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-55	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-200	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-220	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-510	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-550	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-704	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-705	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-710	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-1208	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-4050	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-6620	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-F60	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-F61	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Corning-XF60	U	U	U	U	U	U	U	U	U	U	U	U	U
Dow Guard	U	U	U	U	U	U	U	U	U	U	U	U	U
Dowtherm Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Dowtherm A or E	U	U	U	U	U	U	U	U	U	U	U	U	U
Dowtherm 209, 50% Solution	U	U	U	U	U	U	U	U	U	U	U	U	U
Drinking Water	U	U	U	U	U	U	U	U	U	U	U	U	U
Dry Cleaning Fluids	U	U	U	U	U	U	U	U	U	U	U	U	U
DTE Light Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
E	U	U	U	U	U	U	U	U	U	U	U	U	U
Elco 28-EP Lubricant	U	U	U	U	U	U	U	U	U	U	U	U	U
Epichlorohydrin	U	U	U	U	U	U	U	U	U	U	U	U	U
Epoxy Resins	U	U	U	U	U	U	U	U	U	U	U	U	U
Esam-6 Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Esso Fuel 208	U	U	U	U	U	U	U	U	U	U	U	U	U
Esso Golden Gasoline	U	U	U	U	U	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Esso Motor Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Esso Transmission Fluid (type A)	U	U	U	U	U	U	U	U	U	U	U	U	U
Esso WS3812 (MIL-L-7808A)	U	U	U	U	U	U	U	U	U	U	U	U	U
Esso XP90-EP Lubricant	U	U	U	U	U	U	U	U	U	U	U	U	U
Esstic 42,43	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethanol Amine	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethers	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Acetate-Organic Ester	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Acetoacetate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Acrylate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Acrylic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Alcohol	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Benzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Benzoate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Bromide	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Cellosolve	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Cellulose	B	B	B	B	B	B	B	B	B	B	B	B	B
Ethyl Chloride	B	B	A	B	A	B	A	B	B	B	B	B	B
Ethyl Chlorocarbonate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Chloroformate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Cyclopentane	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Ether	U	U	U	U	C	B	C	B	B	B	B	B	B
Ethyl Formate	U	U	U	U	B	B	B	C	B	B	B	B	B
Ethyl Hexanol	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Mercaptan	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Oxalate	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Pentachlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethyl Silicate	B	B	A	A	A	A	A	A	A	A	B	B	B
Ethylene	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethylene Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Ethylene Chlorohydrin	B	B	B	B	B	B	B	B	B	B	B	B	B
Ethylene Diamine	B	B	A	A	A	A	A	A	A	A	A	A	A
Ethylene Dibromide	U	U	C	C	C	C	C	C	C	C	C	C	C
Ethylene Dichloride	U	U	C	C	C	C	C	C	C	C	C	C	C
Ethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylene Oxide	U	U	C	C	C	C	C	C	C	C	C	C	C
Ethylene Trichloride	U	U	C	C	C	C	C	C	C	C	C	C	C
Ethylmorpholene Stannous Octoate(50/50 mix	U	U	B	B	B	B	B	B	B	B	B	B	B
F													

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Hydrin</i>	<i>Neoprene</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
F-60 Fluid (Dow Corning)	A	A	A	A	A	A	A	A	A	A	A	A	A
F-61 Fluid (Dow Corning)	A	A	A	A	A	A	A	A	A	A	A	A	A
Fatty Acids	C	U	U	A	U	B	A	B	A	A	A	A	A
FC-43 Heptacosofluorotri-butylamine	U	U	U	A	A	A	A	A	A	A	A	A	A
FC-75 Fluorocarbon	U	U	U	A	A	A	A	A	A	A	A	B	A
Ferric Chloride	A	A	A	A	A	A	A	B	A	B	A	A	A
Ferric Nitrate	A	A	A	A	A	A	A	A	A	A	A	C	A
Ferric Sulfate	A	A	A	A	A	A	A	A	A	A	A	B	A
Fish Oil	A	A	A	A	A	A	A	A	A	A	A	A	A
Fluoroboric Acid	A	A	A	A	A	A	A	A	A	A	A	B	B
Fluorine (Liquid)	A	A	C	C	U	U	U	U	U	U	U	U	B
Fluorobenzene	U	U	U	A	U	U	U	U	U	U	U	U	B
Fluorocarbon Oils	U	U	U	A	A	A	U	A	A	A	A	U	B
Fluorolube	U	U	U	A	A	A	A	A	A	A	A	A	B
Fluorinated Cyclic Ethers	U	U	U	A	A	A	A	A	A	A	A	U	B
Flosilicic	A	C	A	A	A	A	A	A	A	A	A	B	U
Formaldehyde	B	C	A	A	A	C	B	C	A	C	B	B	C
Formic Acid	A	A	A	A	B	B	B	A	A	A	A	C	A
Freon,11	U	U	U	B	U	B	A	U	A	U	A	U	B
Freon,12	B	A	B	B	A	A	A	A	A	A	A	U	B
Freon,12 and ASTM-Oil#2(50/50 mixture)	U	U	U	U	U	A	B	B	B	B	B	U	B
Freon,12 and Suniso 4G (50/50 mixture)	U	U	U	U	U	A	B	B	B	B	B	U	B
Freon,13	A	A	A	A	A	A	A	A	A	A	A	U	A
Freon,13B1	A	A	A	A	A	A	A	A	A	A	A	U	A
Freon, 14	A	A	A	A	A	A	A	A	A	A	A	U	A
Freon, 21	U	U	U	U	U	U	B	B	A	U	U	U	U
Freon, 22	A	A	A	A	A	U	U	B	A	U	U	U	U
Freon, 22 and ASTM Oil#2 (50/50 mixture)	U	U	U	U	U	U	U	B	B	B	B	U	B
Freon, 31	B	B	A	A	A	U	U	A	A	B	C	U	U
Freon, 32	A	A	A	A	A	A	A	A	A	A	A	U	A
Freon, 112	U	U	U	U	U	U	B	B	B	B	B	U	A
Freon, 113	U	U	B	U	U	U	A	A	A	A	B	U	B
Freon, 114	A	A	A	A	A	A	A	A	A	A	A	U	B
Freon, 114B2	U	U	U	U	U	U	B	A	A	A	B	U	B
Freon, 115	A	A	A	A	A	A	A	A	A	A	A	B	B
Freon, 142b	A	A	A	A	A	A	A	A	A	A	A	B	U
Freon, 152a	A	A	A	A	A	A	A	A	A	C	A	A	A
Freon, 218	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon, C316	A	A	A	A	A	A	A	A	A	A	A	A	A
Freon, C318	A	A	A	A	A	A	A	A	A	A	A	A	A

**LEGEND**
**A - RECOMMENDED**
**B - MINOR TO MODERATE EFFECT**
**C - MODERATE TO SEVERE**
**U - UNSATISFACTORY**
**BLANK - INSUFFICIENT DATA**
**Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Freon, 502	A	A	B	A	B	B	A	A	B	B	A	A	B
Freon, BF	U	U	U	U	U	U	U	U	U	U	U	U	A
Freon, MF	U	U	U	U	U	U	U	U	U	U	U	U	B
Freon, TF	U	U	U	U	U	U	U	U	U	U	U	U	B
Freon, TA	U	U	U	U	U	U	U	U	U	U	U	U	C
Freon, TC	U	U	U	U	U	U	U	U	U	U	U	U	A
Freon, TMC	U	U	U	U	U	U	U	U	U	U	U	U	A
Freon, T-P35	U	U	U	U	U	U	U	U	U	U	U	U	A
Freon, T-WD602	U	U	U	U	U	U	U	U	U	U	U	U	A
Freon, PCA	U	U	U	U	U	U	U	U	U	U	U	U	B
Fuel Oil	U	U	U	U	U	U	U	U	U	U	U	U	A
Fuel Oil, Acidic	U	U	U	U	U	U	U	U	U	U	U	U	A
Fuel Oil, #6	U	U	U	U	U	U	U	U	U	U	U	U	A
Fumaric Acid	U	U	U	U	U	U	U	U	U	U	U	U	A
Fuming Sulphuric Acid (20/25% Oleum)	U	U	U	U	U	U	U	U	U	U	U	U	A
Furan (Furfuran)	U	U	U	U	U	U	U	U	U	U	U	U	U
Furfural	U	U	U	U	U	U	U	U	U	U	U	U	U
Furfuraldehyde	U	U	U	U	U	U	U	U	U	U	U	U	U
Furaryl Alcohol	U	U	U	U	U	U	U	U	U	U	U	U	U
Furyl Carbinol	U	U	U	U	U	U	U	U	U	U	U	U	C
Fyrquel A60	U	U	U	U	U	U	U	U	U	U	U	U	U
Fyrquel 90, 100, 150, 220, 300,500	U	U	U	U	U	U	U	U	U	U	U	U	B
G													A
Gallic Acid	A	B	B	B	B	B	B	B	B	B	B	B	A
Gasoline	U	U	U	U	U	U	U	U	U	U	U	U	A
Gelatin	A	A	A	A	A	A	A	A	A	A	A	A	A
Girling Brake Fluid	A	A	B	A	B	A	C	B	B	B	B	B	U
Glacial Acetic Acid	B	B	B	B	B	B	B	B	B	B	B	B	U
Glauber's Salt	B	U	B	B	B	B	B	B	B	B	B	B	A
Glucose	A	A	A	A	A	A	A	A	A	A	A	A	A
Glue (Depending on type)	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycerine-Glycerol	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycols	A	A	A	A	A	A	A	A	A	A	A	A	A
Green Sulphate Liquor	B	B	A	A	A	B	B	B	B	B	B	B	A
Gulfcrown Grease	U	U	U	U	U	A	A	B	B	B	B	B	A
Gulf Endurance Oils	U	U	U	U	U	A	A	B	B	B	B	B	A
Gulf FR Fluids (Emulsion)	U	U	U	U	U	A	A	B	B	B	B	B	A
Gulf FRG-Fluids	A	A	A	A	A	A	A	A	A	A	A	C	A
Gulf FRP-Fluids	U	U	U	B	U	B	U	B	U	B	U	C	B
Gulf Harmony Oils	U	U	U	U	U	A	B	B	B	B	B	C	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Gulf High temperature Grease	U	U	U	U	U	U	U	U	U	U	U	U	U
Gulf Legion Oils	U	U	U	U	U	U	U	U	U	U	U	U	U
Gulf Paramount Oils	U	U	U	U	U	U	U	U	U	U	U	U	U
Gulf Security Oils	U	U	U	U	U	U	U	U	U	U	U	U	U
H													
Halothane	U	U	U	U	U	U	U	U	U	U	U	U	U
Halowax Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Hannifin Lube A	U	U	U	U	U	U	U	U	U	U	U	U	U
Heavy Water	U	U	U	U	U	U	U	U	U	U	U	U	U
HEF-2 (High Energy Fuel)	U	U	U	U	U	U	U	U	U	U	U	U	U
Helium	U	U	U	U	U	U	U	U	U	U	U	U	U
N-Heptane	U	U	U	U	U	U	U	U	U	U	U	U	U
N-Hexaldehyde	U	U	U	U	U	U	U	U	U	U	U	U	U
Hexane	U	U	U	U	U	U	U	U	U	U	U	U	U
N-Hexane-1	U	U	U	U	U	U	U	U	U	U	U	U	U
Hexyl Alcohol	U	U	U	U	U	U	U	U	U	U	U	U	U
High Viscosity Lubricant, U4	U	U	U	U	U	U	U	U	U	U	U	U	U
High Viscosity Lubricant, H2	U	U	U	U	U	U	U	U	U	U	U	U	U
Hilo MS #1	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 271 (Water and Glycol base)	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 620 (Water/Clycol)	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 1010, Phosphate Ester	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 1055, Phosphate Ester	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 1120, Phosphate Ester	U	U	U	U	U	U	U	U	U	U	U	U	U
Houghto-Safe 5040 (Water/Oil emulsion)	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydraulic Oil (Petroleum Base)	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrazine	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrobromic Acid	A	U	U	U	U	U	U	U	U	U	U	U	U
Hydrobromic Acid 40%	A	U	U	U	U	U	U	U	U	U	U	U	U
Hydrocarbon (Saturated)	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid Hot 37%	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid Cold 37%	B	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid 3 Molar	C	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid Concentrated	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrocyanic Acid	B	U	U	U	U	U	U	U	U	U	U	U	U
Hydro-Drive, MIH-50 (Petroleum Base)	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydro-Drive, MIH-10 (Petroleum Base)	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrofluoric Acid, 65% Max. Cold	B	U	U	U	U	U	U	U	U	U	U	U	U
Hydrofluoric Acid, 65% Min. Cold	U	U	U	U	U	U	U	U	U	U	U	U	U
Hydrofluoric Acid ,65% Max. Hot	U	U	U	U	U	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>								
	<i>Fluorosilicone</i>			<i>Silicone</i>			<i>Polysulfide</i>		
	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Hydrofluoric Acid ,65% Min.. Hot	U	U	U	U	U	U	U	U	U
Hydroflosilicic Acid	A	B	A	A	B	B	B	C	A
Hydrogen Gas, Cold	B	B	A	A	A	A	A	C	C
Hydrogen Gas, Hot	B	B	A	A	A	A	A	C	B
Hydrogen Peroxide (1)	B	B	A	A	B	B	B	C	B
Hydrogen Peroxide 90% (1)	B	U	C	C	U	U	U	U	U
Hydrogen Sulfide Dry, Cold	A	A	A	A	A	A	A	B	C
Hydrogen Sulfide Dry, Hot	A	U	A	A	U	U	B	C	C
Hydrogen Sulfide Wet, Cold	U	U	A	A	U	U	B	C	C
Hydrogen sulfide Wet, Hot	U	U	A	A	U	U	B	C	C
Hydrolube-Water/Ethylene Glycol	B	U	A	B	A	A	B	B	B
Hydroquinone	B	U	B	U	U	U	B	B	B
Hydyne	B	B	B	A	B	B	B	B	B
Hyjet	U	U	B	B	A	U	U	U	U
Hyjet III	U	U	B	B	A	U	U	U	U
Hyjet S	U	U	B	B	A	U	U	U	U
Hyjet W	U	U	B	B	A	U	U	U	U
Hypochlorous Acid	B	U	B	B	B	U	U	U	U
I									
Industron FF44	U	U	U	U	A	A	B	B	A
Industron FF48	U	U	U	U	A	A	B	B	A
Industron FF53	U	U	U	U	A	A	B	B	A
Industron FF80	U	U	U	U	A	A	B	B	A
Iodine	B	U	B	B	B	U	B	B	A
Iodine Pentafluoride	U	U	A	A	A	U	U	U	U
Iodoform	U	U	U	U	A	U	U	U	U
Isobutyl Alcohol	A	B	A	A	B	A	A	B	A
Iso-Butyl N-Butyrate	A	U	A	A	U	A	U	U	A
Isododecane	U	U	U	U	U	U	B	A	A
Iso-Octane	U	U	U	U	U	U	B	B	A
Isophorone (Ketone)	U	U	A	A	A	U	U	U	U
Isopropanol	A	U	B	A	A	B	B	A	B
Isopropyl Acetate	U	U	B	B	B	U	U	U	U
Isopropyl Alcohol	A	B	A	A	B	A	B	A	B
Isopropyl Chloride	U	U	U	U	U	U	U	U	A
Isopropyl Ether	U	U	U	U	B	C	B	A	C
J									
JP 3 (MIL-J-5624)	U	U	U	U	A	U	B	B	A
JP 4 (MIL-J-5624)	U	U	U	U	A	U	B	B	B
JP 5 (MIL-J-5624)	U	U	U	U	A	U	B	B	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
JP 6 (MIL-J-25656)													
JP X (MIL-F-25604)													
K													
Kel F Liquids													
Kerosene													
Keystone #87HX-Grease													
L													
Lactams-Amino Acids													
Lactic Acid, Cold													
Lactic Acid, Hot													
Lacquers													
Lacquer Solvents													
Lactic Acids													
Lard, Animal Fats													
Lavender Oil													
Lead Acetate													
Lead Nitrate													
Lead Sulphamate													
Lehigh X1169													
Lehigh X1170													
Light Grease													
Ligroin (Petroleum Ether or Benzine)													
Lime Bleach													
Lime Sulphur													
Lindol, Hydraulic Fluid (Phosphate ester type)													
Linoleic Acid													
Linseed Oil													
Liquid Oxygen													
Liquid Petroleum Gas (LPG)													
Liquimoly													
Lubricating Oils, Di-ester													
Lubricating Oils, Petroleum Base													
Lubricating Oils, SAE 10, 20, 30, 40, 50													
Lye Solutions													
M													
Magnesium Chloride	A	A	A	A	A	A	A	A	A	A	C	A	A
Magnesium Hydroxide	B	B	A	A	B	A	B	A	B	B	C	A	A
Magnesium Sulphate	B	B	A	A	A	A	A	A	A	B	A	A	A
Magnesium Sulphite	B	B	A	A	A	A	A	A	A	B	A	A	A
Magnesium Salts	A	A	A	A	A		A	A	A	A	A	A	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Malathion	B	B	B	B	U	U	U	U	B	U	U	U	A
Maleic Acid	A	A	A	B	U	U	U	U	U	U	U	U	A
Maleic Anhydride	A	A	A	C	U	U	U	U	U	U	U	U	A
Malic Acid	A	A	A	C	U	U	U	U	U	U	U	U	A
MCS 312	A	A	A	C	U	U	U	U	U	U	U	U	A
MCS 352	A	A	A	C	U	U	U	U	U	U	U	U	A
MCS 463	A	A	A	C	U	U	U	U	U	U	U	U	A
Mercuric Chloride	A	A	A	A	U	U	U	U	U	U	U	U	A
Mercury	A	A	A	A	U	U	U	U	U	U	U	U	A
Mercury Vapors	A	A	A	A	U	U	U	U	U	U	U	U	A
Mesityl Oxide (Ketone)	A	A	A	A	U	U	U	U	U	U	U	U	A
Methane	A	A	A	B	U	U	U	U	U	U	U	U	B
Methanol	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Acetate	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Acetoacetate	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Acrylate	A	A	A	B	U	U	U	U	U	U	U	U	A
Methylacrylic Acid	A	A	A	B	U	U	U	U	U	U	U	U	C
Methyl Alcohol	A	A	A	B	U	U	U	U	U	U	U	U	C
Methyl Benzoate	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Bromide	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Butyl Ketone	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Carbonate	A	A	A	B	U	U	U	U	U	U	U	U	B
Methyl Cellosolve	A	A	A	B	U	U	U	U	U	U	U	U	B
Methyl Cellulose	B	B	B	B	U	U	U	U	U	U	U	U	B
Methyl Chloride	B	B	B	C	U	U	U	U	U	U	U	U	B
Methyl Chloroformate	B	B	B	C	U	U	U	U	U	U	U	U	B
Methyl D-Bromide	B	B	B	C	U	U	U	U	U	U	U	U	A
Methyl Cyclopentane	B	B	B	C	U	U	U	U	U	U	U	U	B
Methylene Chloride	B	B	B	C	U	U	U	U	U	U	U	U	B
Methylene Dichloride	B	B	B	C	U	U	U	U	U	U	U	U	B
Methyl Ether	A	A	A	B	U	U	U	U	U	U	U	U	A
Methyl Ethyl Ketone (MEK)	A	A	A	B	U	U	U	U	U	U	U	U	U
Methyl Ethyl Ketone Peroxide	A	A	A	B	U	U	U	U	U	U	U	U	U
Methyl Formate	A	A	A	B	U	U	U	U	U	U	U	U	B
Methyl Isobutyl Ketone (MIBK)	A	A	A	B	U	U	U	U	U	U	U	U	U
Methyl Isopropyl Ketone	A	A	A	B	U	U	U	U	U	U	U	U	C
Methyl Methacrylate	A	A	A	B	U	U	U	U	U	U	U	U	B
Methyl Oleate	A	A	A	B	U	U	U	U	U	U	U	U	B
Methyl Salicylate	A	A	A	B	U	U	U	U	U	U	U	U	A
MIL-L-644B	C	C	C	C	C	A	A	C	C	C	C	C	C

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
MIL-L-2104B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-2105B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-2108	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type I Fuel	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type II Fuel	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type III Fuel	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type IV	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type V	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type VI	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-3136B, Type VII	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-3150A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-3278	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-3503	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-3545B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-C-4339C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-4343B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-5020A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-J-5161F	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-C-5545A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-5559A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-5566	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-5572	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-5602	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-5606B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-J-5624, JP-3	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-J-5624G, JP-4	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-J-5624G, JP-5	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-6081C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-6082C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-6083C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-6085A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-6086B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-A-6091	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-6387A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-C-6529C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-7024A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-7083	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-7118A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-7187	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-7421A	U	U	U	U	U	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
MIL-H-7644	B	A	A	C	C	B	B	B	B	B	B	B	A
MIL-L-7645	U	U	U	U	U	U	U	U	U	U	U	U	A
MIL-G-7711A	U	U	U	U	U	U	U	U	U	U	U	U	A
MIL-L-7808F	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-7870A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-C-8188C	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-A-8243B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-8383B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-H-8446B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-I-8660B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-9000F	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-T-9188B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-9236B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-E-9500	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-10295A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-10324A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-G-10924B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-11734B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-O-11773	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-P-12098	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-H-13862	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-H-13866A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-H-13910B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-H-13919A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-14107B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-15016	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-15017	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-15018B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-15019C	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-15719A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-G-15793	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-F-16884	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-F-16929A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-16958A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-F-17111	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-17331D	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-17353A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-17672B	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-L-18486A	U	U	U	U	U	U	U	U	U	U	U	U	B
MIL-G-18709A	U	U	U	U	U	U	U	U	U	U	U	U	B

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
MIL-H-19457B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-19605	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-19701	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-21260	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-21568A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-22072	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-22251	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-22396	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-23699A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-23827A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-25013D	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-25172	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-25336B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-25524A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-25537A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-25558B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-25576C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-25598	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-F-25656B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-25681C	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-25760A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-25968	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-26087A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-27343	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-P-27402	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-27601A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-G-27617	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-I-27686D	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-27694A	U	U	U	U	U	U	U	U	U	U	U	U	U
MUL-L-46000A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-46001A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-L-46002	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-46004	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-P-46046A	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-81019B	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-S-81087	U	U	U	U	U	U	U	U	U	U	U	U	U
MIL-H-83282	U	U	U	U	U	U	U	U	U	U	U	U	U
Milk	U	U	U	U	U	U	U	U	U	U	U	U	U
Minerals Oils	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobil 24 DTE	U	U	U	U	U	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Mobil HF	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobil Delvac 1100, 1110, 1120, 1130	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobil Nyvac 20 and 30	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobil Velocite C	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobilgas WA200, Type A, Automatic trans.flu	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobil Oil SAE 20	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobiltherm 600	U	U	U	U	U	U	U	U	U	U	U	U	U
Mobilux	U	U	U	U	U	U	U	U	U	U	U	U	U
Mono Bromobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Mono Chlorobenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Mono Ethanolamine	U	U	U	U	U	U	U	U	U	U	U	U	U
Monomethyl Aniline	U	U	U	U	U	U	U	U	U	U	U	U	U
Monomethylether	U	U	U	U	U	U	U	U	U	U	U	U	U
Monomethyl Hydrazine	U	U	U	U	U	U	U	U	U	U	U	U	U
Mononitrotoluene & Dinitrotoluene(40/60 Mix.)	U	U	U	U	U	U	U	U	U	U	U	U	U
Monovinyl Acetylene	B	B	A	A	A	A	A	A	A	B	B	B	C
Mopar Brake Fluid	B	B	A	B	A	C	B	B	B	B	B	C	U
Mustard Gas	A	U	U	U	U	U	U	U	U	U	U	U	U
N	U	U	U	U	U	U	U	U	U	U	U	U	U
Naptha	U	U	U	U	U	U	U	U	U	U	U	U	U
Naphthalene	U	U	U	U	U	U	U	U	U	U	U	U	U
Naphthenic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Natural Gas	C	C	C	C	C	C	C	C	C	C	C	C	C
Neatsfoot Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Neon	A	U	U	U	U	U	U	U	U	U	U	U	U
Neville Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Nickel Acetate	A	U	A	A	A	B	B	B	B	B	B	B	U
Nickel Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Nickel Salts	A	A	A	A	A	A	A	A	A	B	B	B	A
Nickel Sulfate	B	B	A	A	A	A	A	A	A	A	A	C	A
Niter Cake	A	A	A	A	A	A	A	A	A	A	A	A	A
Nitric Acid (1) 3 Molar	U	U	U	U	U	B	B	B	B	B	B	B	C
Nitric Acid (1) Concentrated	U	U	U	U	C	U	U	U	U	U	U	U	U
Nitric Acid Dilute	U	U	U	B	B	B	B	U	U	U	U	U	B
Nitric Acid (1) Red Fuming (RFNA)	U	U	B	B	U	U	U	U	U	U	U	U	C
Nitric Acid (1) Inhibited Red Fuming (IRFNA)	U	U	B	B	U	U	U	U	U	U	U	U	B
Nitrobenzene	U	U	B	C	C	U	U	U	U	U	U	U	B
Nitrobenzine													A
Nitroethane	B	B	B	B	B	U	U	C	C	C	C	U	U
Nitrogen	A	A	A	A	A	A	A	A	A	A	A	A	A

**LEGEND**
**A - RECOMMENDED**
**B - MINOR TO MODERATE EFFECT**
**C - MODERATE TO SEVERE**
**U - UNSATISFACTORY**
**BLANK - INSUFFICIENT DATA**
**Chemical**

	<i>Fluoro Elastomers</i>							
	<i>Fluorosilicone</i>		<i>Silicone</i>		<i>Polysulfide</i>		<i>Urethane, Polyurethane</i>	
	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Nitrogen (Tetroxide (N <sub>2</sub> O <sub>4</sub> ) (1)	U	U	U	U	U	U	U	U
Nitromethane	U	U	U	U	U	U	U	U
Nitropropane	U	U	U	U	U	U	U	U
O								
O-A-548A	B	U	A	U	U	U	U	U
O-T-634b	U	U	U	U	U	U	U	U
Octachloro Toluene	B	U	U	U	U	U	U	U
Octadecane	B	U	U	U	U	U	U	U
N-Octane	B	U	U	U	U	U	U	U
Octyl Alcohol	B	U	U	U	U	U	U	U
Oleic Acid	B	U	U	U	U	U	U	U
Oleum (Fuming Sulfuric Acid)	B	U	U	U	U	U	U	U
Oleum Spirits	B	U	U	U	U	U	U	U
Olive Oil	B	U	U	U	U	U	U	U
Oronite 8200	B	U	U	U	U	U	U	U
Oronite 8515	B	U	U	U	U	U	U	U
Orthochloro Ethyl Benzene	B	U	U	U	U	U	U	U
Ortho-Dichlorobenzene	B	U	U	U	U	U	U	U
OS 45 Type III (OS45)	B	U	U	U	U	U	U	U
OS 45 Type IV (OS45-1)	B	U	U	U	U	U	U	U
OS 70	B	U	U	U	U	U	U	U
Oxalic Acid	B	U	U	U	U	U	U	U
Oxygen, Cold	B	U	U	U	U	U	U	U
Oxygen, Cold 200-400 F	B	U	U	U	U	U	U	U
Ozone	B	U	U	U	U	U	U	U
P								
P-S-661b	U	U	U	U	U	U	U	U
P-D-680	U	U	U	U	U	U	U	U
Paint Thinner- Duco	U	U	U	U	U	U	U	U
Palmitic Acid	B	U	U	U	U	U	U	U
Para-dichlorobenzene	B	U	U	U	U	U	U	U
Par-al-Ketone	B	U	U	U	U	U	U	U
Parker O Lube	B	U	U	U	U	U	U	U
Peanut Oil	B	U	U	U	U	U	U	U
Pentane, 2 Methyl	B	U	U	U	U	U	U	U
Pentane,2-4 dimethyl	B	U	U	U	U	U	U	U
Pentane, 3 Methyl	B	U	U	U	U	U	U	U
N-Pentane	C	U	U	U	U	U	U	U
Perchloric Acid	B	U	U	U	U	U	U	U
Perchloroethylene	B	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Petroleum Oil, Crude	U	U	U	U	U	U	U	U	U	U	U	U	U
Petroleum Oil, Below 250 F	U	U	U	U	U	U	U	U	U	U	U	U	U
Petroleum Oil, Above 250 F	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenol	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenol, 70%/30% H2O	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenol, 85%/15% H2O	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenylbenzene	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenyl Ethyl Ether	U	U	U	U	U	U	U	U	U	U	U	U	U
Phenyl Hydrazine	U	U	U	U	U	U	U	U	U	U	U	U	U
Phorone	U	U	U	U	U	U	U	U	U	U	U	U	U
Phosphoric Acid 20%	U	U	U	U	U	U	U	U	U	U	U	U	U
Phosphoric Acid 45%	U	U	U	U	U	U	U	U	U	U	U	U	U
Phosphoric Acid, 3 Molar	U	U	U	U	U	U	U	U	U	U	U	U	U
Phosphoric Acid, Concentrated	U	U	U	U	U	U	U	U	U	U	U	U	U
Phosphorous Trichloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Pickling Solution	U	U	U	U	U	U	U	U	U	U	U	U	U
Picric Acid, H2O Solution	U	U	U	U	U	U	U	U	U	U	U	U	U
Picric Acid, Molten	U	U	U	U	U	U	U	U	U	U	U	U	U
Pinene	U	U	U	U	U	U	U	U	U	U	U	U	U
Pine Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Piperidine	U	U	U	U	U	U	U	U	U	U	U	U	U
Plating Solutions, Chrome	U	U	U	U	U	U	U	U	U	U	U	U	U
Plating Solutions, Others	U	U	U	U	U	U	U	U	U	U	U	U	U
Pneumatic Service	U	U	U	U	U	U	U	U	U	U	U	U	U
Polyvinyl Acetate Emulsion	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Acetate	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Cupro Cyanide	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Cyanide	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Dichromate	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Hydroxide	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Nitrate	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium salts	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Sulphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Sulphite	U	U	U	U	U	U	U	U	U	U	U	U	U
Prestone Antifreeze	U	U	U	U	U	U	U	U	U	U	U	U	U
PRL-High Temp. Hydro. Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Producer Gas	U	U	U	U	U	U	U	U	U	U	U	U	U
Propane	U	U	U	U	U	U	U	U	U	U	U	U	U
Propane Propionitrile	U	U	U	U	U	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Propyl Acetate	U	U	U	U	U	U	U	U	U	U	U	U	U
N-Propyl Acetone	U	U	U	U	U	U	U	U	U	U	U	U	U
Propyl Alcohol	U	U	U	U	U	U	U	U	U	U	U	U	U
Propyl Nitrate	U	U	U	U	U	U	U	U	U	U	U	U	U
Propylene	U	U	U	U	U	U	U	U	U	U	U	U	U
Propylene Oxide	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyranol, Transformer oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyranol	U	U	U	U	U	U	U	U	U	U	U	U	U
Pydraul, 10E, 29ELT	U	U	U	U	U	U	U	U	U	U	U	U	U
Pydraul, 30E,50E, 65E, 90E	U	U	U	U	U	U	U	U	U	U	U	U	U
Pydraul ,115 E	U	U	U	U	U	U	U	U	U	U	U	U	U
Pydraul, 230E, 312C, 540C	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyridine Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyrogard 42, 43, 53, 55 (Phosphate Ester)	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyrogard, C, D	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyroligneous Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyrolube	U	U	U	U	U	U	U	U	U	U	U	U	U
Pyrrole	C	C	C	C	C	C	C	C	C	C	C	C	C
R													
Radiation	C	C	C	C	C	C	C	C	C	C	C	C	C
Rapeseed Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Red Oil (MIL-H-5606)	U	U	U	U	U	U	U	U	U	U	U	U	U
Red Line 100 Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
RJ-1 (MIL-F-25558)	U	U	U	U	U	U	U	U	U	U	U	U	U
RP-1 (MIL-R-25576)	U	U	U	U	U	U	U	U	U	U	U	U	U
S													
Sal Ammoniac	A	A	A	A	A	A	A	A	A	A	A	B	A
Salicylic Acid	A	B	A	A	A	B	A	B	A	B	B	A	A
Salt Water	A	A	A	A	A	A	A	A	A	B	B	A	A
Santo Safe 300	U	U	C	C	C	A	U	U	U	U	U	A	A
Sewage	B	B	B	B	B	B	B	B	B	B	B	B	A
Shell Alvania Grease #2	U	U	U	U	U	U	U	U	U	U	U	B	A
Shell Carnea 19 and 29	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Diala	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Iris 905	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Iris 3XF Mine Fluid (Fire resist. Hydro.)	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Iris Tellus #27, Pet. Base	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Iris Tellus #33	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Iris UMF (5% Aromatic)	U	U	U	U	U	U	U	U	U	U	B	B	A
Shell Lo Hydrax 27 and 29	U	U	U	U	U	U	U	U	U	U	B	B	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Shell Macoma 72	U	U	U	U	U	U	U	U	U	U	U	U	U
Silicate Esters	U	U	U	U	U	U	U	U	U	U	U	U	U
Silicone Greases	A	A	A	A	A	A	A	A	A	A	A	A	A
Silicone Oils	A	A	A	A	A	A	A	A	A	A	A	A	A
Silver Nitrate	A	A	A	A	A	A	A	A	A	A	A	A	A
Sinclair Opaline CX-Ep Lube	U	U	U	U	U	U	U	U	U	U	U	U	U
Skelly, Solvent B, C, E	U	U	U	U	U	U	U	U	U	U	U	U	U
Skydrol 500	U	U	U	U	U	U	U	U	U	U	U	U	U
Skydrol 7000	U	U	U	U	U	U	U	U	U	U	U	U	U
Soap Solutions	B	B	B	B	B	B	B	B	B	B	B	B	B
Socony Mobile Type A	U	U	U	U	U	U	U	U	U	U	U	U	U
Socony Vacuum AMV AC781 (Grease)	U	U	U	U	U	U	U	U	U	U	U	U	U
Socony Vacuum PD959B	U	U	U	U	U	U	U	U	U	U	U	U	U
Soda Ash	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Acetate	A	U	A	A	A	B	B	B	B	B	B	B	B
Sodium Bicarbonate (Baking Soda)	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Bisulfite	A	B	A	A	A	A	A	A	A	A	A	A	A
Sodium Borate	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Carbonate (Soda Ash)	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Chloride	A	A	A	A	A	A	A	A	A	A	C	A	A
Sodium Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Hydroxide	A	A	A	A	B	B	B	B	B	B	B	B	B
Sodium Hypochlorite	C	C	B	B	B	A	B	B	B	B	B	B	B
Sodium Metaphosphate	A	A	A	A	A	A	B	B	B	B	B	B	B
Sodium Nitrate	B	B	A	A	B	B	B	B	B	B	B	B	B
Sodium Perborate	B	B	A	A	B	B	B	B	B	B	B	B	B
Sodium Peroxide	B	B	A	A	B	B	B	B	B	B	B	B	B
Sodium Phosphate (Mono)	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Phosphate (Dibasic)	A	A	A	A	A	A	B	B	B	B	B	B	B
Sodium Phosphate (Tribasic)	A	A	A	A	A	A	B	B	B	B	B	B	B
Sodium Salts	A	A	A	A	A	A	B	B	B	B	B	B	B
Sodium Silicate	A	A	A	A	A	A	B	B	B	B	B	B	B
Sodium Sulphate	B	B	A	A	A	A	A	A	A	A	A	A	A
Sodium Sulphide	B	B	A	A	A	A	A	A	A	A	A	A	A
Sodium Sulfite	B	B	A	A	A	A	A	A	A	A	A	A	A
Sodium Thiosulfate	B	B	A	A	B	B	A	A	A	A	B	B	B
Sovasol #1, 2, and 3	U	U	U	U	U	U	B	B	B	B	B	B	B
Sovasol #73 and 74	U	U	U	U	U	U	B	B	B	B	B	B	B
Soybean Oil	U	U	U	C	C	A	C	C	C	C	B	B	B
Spry	U	U	B	B	A	A	B	B	B	B	A	A	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
SR-6 Fuel	U	U	U	U	U	U	U	U	U	U	U	U	U
SR-10 Fuel	U	U	U	U	U	U	U	U	U	U	U	U	U
Standard Oil Mobilube GX90-EP Lube	U	U	U	U	U	U	U	U	U	U	U	U	U
Stannic Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Stannic Chloride 50%	U	U	U	U	U	U	U	U	U	U	U	U	U
Stannous Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Stauffer 7700	U	U	U	U	U	U	U	U	U	U	U	U	U
Steam, Below 350 F	U	U	U	U	U	U	U	U	U	U	U	U	U
Steam, Above 350 F	U	U	U	U	U	U	U	U	U	U	U	U	U
Stearic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Stoddard Solvent	U	U	U	U	U	U	U	U	U	U	U	U	U
Styrene	U	U	U	U	U	U	U	U	U	U	U	U	U
Styrene (Monomer)	U	U	U	U	U	U	U	U	U	U	U	U	U
Sucrose Solutions	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfite Liquors	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Dioxide, Wet	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Dioxide, Dry	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Dioxide, Liquidified under pressure	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Hexafluoride	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Liquors	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Molten	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfur Trioxide	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfuric Acid Dilute	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfuric Acid Concentrated	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfuric Acid 20% Oleum	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfuric Acid 3 Molar	U	U	U	U	U	U	U	U	U	U	U	U	U
Sulfurous Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Sunoco SAE 10	U	U	U	U	U	U	U	U	U	U	U	U	U
Sunoco #3661	U	U	U	U	U	U	U	U	U	U	U	U	U
Sunoco All purpose grease	U	U	U	U	U	U	U	U	U	U	U	U	U
Sunsafe (Fire resist. Hydr. Fluid)	U	U	U	U	U	U	U	U	U	U	U	U	U
Super Shell Gas	U	U	U	U	U	U	U	U	U	U	U	U	U
Swan Finch EP Lube	U	U	U	U	U	U	U	U	U	U	U	U	U
Swan Finch Hypoid-90	U	U	U	U	U	U	U	U	U	U	U	U	U
T													
TT-N-95a	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-N-97B	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-I-735b	A	A	A	A	A	A	B	B	B	C	C	C	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
TT-S-735, Type I	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-S-735, Type II	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-S-735, Type III	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-S-735, Type IV	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-S-735, Type V	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-S-735, Type VI	U	U	U	U	U	U	U	U	U	U	U	U	U
TT-T-656b	U	U	U	U	U	U	U	U	U	U	U	U	U
Tannic Acid	A	B	A	A	A	A	B	B	B	B	B	B	A
Tannic Acid, 10%	A	B	A	A	A	A	B	B	B	B	B	B	A
Tar Bituminous	U	U	U	U	U	U	U	U	U	U	U	U	U
Tartaric Acid	U	A	B	B	B	B	B	B	B	B	B	B	A
Terpineol	U	B	C	B	B	B	B	B	B	B	B	B	A
Tertiary Butyl Alcohol	B	B	C	B	B	B	B	B	B	B	B	B	A
Tertiary Butyl Catechol	U	C	B	B	B	B	B	B	B	B	B	B	A
Tertiary Butyl Mercaptan	U	U	U	U	U	U	U	U	U	U	U	U	U
Tetrabromomethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Tetrabutyl Titanate	B	B	B	B	B	B	B	B	B	B	B	B	A
Tetrachloroethylene	B	B	B	B	B	B	B	B	B	B	B	B	A
Tetraethyl Lead	U	U	U	U	U	U	U	U	U	U	U	U	U
Tetraethyl Lead "Blend"	U	U	U	U	U	U	U	U	U	U	U	U	U
Tetrahydrofuran	U	U	U	U	U	U	U	U	U	U	U	U	U
Tetralin	U	U	U	U	U	U	U	U	U	U	U	U	U
Texaco 3450 Gear Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Texaco Capella A and AA	U	U	U	U	U	U	U	U	U	U	U	U	U
Texaco Meropa #3	U	U	U	U	U	U	U	U	U	U	U	U	U
Texaco Regal B	U	U	U	U	U	U	U	U	U	U	U	U	U
Texaco Uni-Temp. Grease	U	U	U	U	U	U	U	U	U	U	U	U	U
Texamatic 1581 Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Texamatic 3401 Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Texamatic 3525 Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Texamatic 3528 Fluid	U	U	U	U	U	U	U	U	U	U	U	U	U
Texas 1500 Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Thiokol TP-90B	U	U	U	U	U	U	U	U	U	U	U	U	U
Thiokol TP-95	U	U	U	U	U	U	U	U	U	U	U	U	U
Thionyl Chloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Tidewater Oil-Beedol	U	U	U	U	U	U	U	U	U	U	U	U	U
Tidewater-Oil-Multigear 140, EP Lube	U	U	U	U	U	U	U	U	U	U	U	U	U
Titanium Tetrachloride	U	U	U	U	U	U	U	U	U	U	U	U	U
Toluene	U	U	U	U	U	U	U	U	U	U	U	U	U
Toluene Diisocyanide	U	U	U	B	B	U	U	U	U	U	U	U	U

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA****Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Transformer Oil	A	A	B	B	A	A	A	B	A	A	B	B	A
Transmission Fluid Type A	A	A	U	U	A	B	B	B	A	A	B	C	A
Triacetin	U	U	U	U	U	U	U	U	U	U	U	U	U
Triaryl Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Tributoxyethyl Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Tributyl Mercaptan	U	U	U	U	U	U	U	U	U	U	U	U	U
Tributyl Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Trichloroacetic Acid	U	U	U	U	U	U	U	U	U	U	U	U	U
Trichloroethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Trichloroethylene	U	U	U	U	U	U	U	U	U	U	U	U	U
Tricresyl Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Triethanol Amine	U	U	U	U	U	U	U	U	U	U	U	U	U
Triethyl Aluminum	U	U	U	U	U	U	U	U	U	U	U	U	U
Triethyl Borane	U	U	U	U	U	U	U	U	U	U	U	U	U
Trifluoroethane	U	U	U	U	U	U	U	U	U	U	U	U	U
Trinitrotoluene	U	U	U	U	U	U	U	U	U	U	U	U	U
Trioctyl Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Tripoly Phosphate	U	U	U	U	U	U	U	U	U	U	U	U	U
Tung Oil (China Wood Oil)	U	U	U	U	U	U	U	U	U	U	U	U	U
Turbine Oil	U	U	U	U	U	U	U	U	U	U	U	U	U
Turbine Oil #15 (MIL-L-7808A)	U	U	U	U	U	U	U	U	U	U	U	U	U
Turbo Oil #35	U	U	U	U	U	U	U	U	U	U	U	U	U
Turpentine	U	U	U	U	U	U	U	U	U	U	U	U	U
Type I Fuel (MIL-S-3136)	U	U	U	U	U	U	U	U	U	U	U	U	U
Type II Fuel (MIL-S-3136)	U	U	U	U	U	U	U	U	U	U	U	U	U
Type III Fuel (MIL-S-3136)	U	U	U	U	U	U	U	U	U	U	U	U	U
U													
Ucon Hydrolube J-4													
Ucon Lubricant LB-65	B	B	A	A	A	A	A	A	B	B	A	A	A
Ucon Lubricant LB-135	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant LB-285	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant LB-300	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant LB-625	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant LB-1145	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB55	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB100	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB260	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB660	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Lubricant 50-HB5100	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Oil LB-385	A	A	A	A	A	A	A	A	A	A	A	A	A

**LEGEND****A - RECOMMENDED****B - MINOR TO MODERATE EFFECT****C - MODERATE TO SEVERE****U - UNSATISFACTORY****BLANK - INSUFFICIENT DATA*****Chemical***

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Ucon Oil LB-400X	A	A	A	A	A	A	A	A	A	A	A	A	A
Ucon Oil 50-HB-280X (Polyacrylon Glycol De	A	A	A	A	A	A	A	A	A	A	A	A	A
Univis 40 (Hydr. Fluid)	A	A	A	A	A	A	A	A	A	A	A	A	A
Univolt #35 (Mineral Oil)	A	A	A	A	A	A	A	A	A	A	A	A	A
Unsymmetrical Dimethyl Hydrazine (UDMH)	A	A	A	A	A	A	A	A	A	A	A	A	A
V													
VV-B-680	B	A	B	A	B	B	B	B	B	B	B	B	B
VV-G-632	U	U	U	U	U	A	A	A	A	A	A	C	A
VV-G-671c	U	U	U	U	U	A	A	A	A	A	A	C	A
VV-H-910	B	A	B	A	C	B	B	B	B	B	B	C	B
VV-I-530a	U	U	U	U	A	A	B	C	B	B	B	U	A
VV-K-211d	U	U	U	U	U	A	A	C	B	B	B	U	A
VV-K-220a	U	U	U	U	U	A	A	B	C	B	B	U	A
VV-L-751b	U	U	U	U	U	B	B	B	B	B	B	U	A
VV-L-800	U	U	U	U	U	A	A	B	B	B	B	U	A
VV-L-800	U	U	U	U	U	A	A	B	B	B	B	U	A
VV-L-820b	U	U	U	U	U	A	A	B	B	B	B	U	A
VV-L-825a, Type I	U	U	U	U	U	A	A	A	A	A	A	U	A
VV-L-825a, Type II	U	U	U	U	U	A	A	A	A	A	A	U	A
VV-L-825a, Type III	U	U	U	U	U	B	B	B	B	B	B	U	A
VV-O-526	U	U	U	U	U	A	A	A	A	A	A	U	A
VV-P-216a	U	U	U	U	U	A	A	B	B	B	B	U	A
VV-P-236	U	U	U	U	U	B	B	B	B	B	B	U	A
Varnish	U	U	U	U	U	B	B	B	B	B	B	U	A
Vegetable Oil	U	U	U	U	U	C	A	C	A	A	A	U	A
Versilube	A	A	A	A	A	B	A	B	A	A	A	U	A
Vinegar	B	B	A	A	B	B	B	B	B	B	B	U	A
Vinyl Chloride	U	U	U	U	U	B	B	B	B	B	B	U	A
W													
Wagner 21B Brake Fluid													
Water	A	A	A	A	A	A	A	B	A	A	A	U	A
Wemco C	U	U	U	U	U	A	A	B	A	A	A	U	A
Whiskey and Wines	A	A	A	A	A	A	A	B	A	A	A	U	A
White Pine Oil	U	U	U	U	U	B	B	B	B	B	B	U	A
White Oil	U	U	U	U	U	A	A	B	A	A	A	U	A
Wolmar Salt	A	A	A	A	A	A	A	B	A	A	A	U	A
Wood Alcohol	A	A	A	A	A	A	A	B	A	A	B	A	U
Wood Oil	U	U	U	U	U	A	A	B	C	B	B	U	A
X	U	U	U	U	U	U	U	U	U	U	B	U	A
Xylene	U	U	U	U	U	U	U	U	U	U	B	U	A

**LEGEND**

- A - RECOMMENDED**  
**B - MINOR TO MODERATE EFFECT**  
**C - MODERATE TO SEVERE**  
**U - UNSATISFACTORY**  
**BLANK - INSUFFICIENT DATA**

**Chemical**

	<i>Fluoro Elastomers</i>	<i>Fluorosilicone</i>	<i>Silicone</i>	<i>Polysulfide</i>	<i>Urethane, Polyurethane</i>	<i>Hypalon</i>	<i>Neoprene</i>	<i>Hydrin</i>	<i>Buna-N, Nitrile, NBR</i>	<i>EPR, EPT, EPDM</i>	<i>Butyl</i>	<i>SBR, GRS</i>	<i>Natural Rubber</i>
Xylenes-Mixed-Aromatic-Amines	U	U	U	U	U	U	U	U	U	U	U	U	U
Xylool	U	U	U	U	U	U	U	U	U	U	U	U	U
Xenon	A	A	A	A	A	A	A	A	A	A	A	A	A
Z													
Zeolites	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Acetate	A	A	U	A	A	A	B	A	A	A	A	U	A
Zinc Chloride	A	A	A	A	A	A	A	A	A	A	A	C	U
Zinc Salts	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Sulfate	B	B	A	A	A	A	A	A	A	A	A	A	A