
# **Geometry of Crystals**


Crystal is a solid composed of atoms, ions or molecules that demonstrate long range periodic order in three dimensions


# The Crystalline State


State of Matter	Fixed Volume	Fixed Shape	Order	Properties
Gas	No	No	No	Isotropic
Liquid	Yes	No	Short-range	Isotropic
Solid (amorphous)	Yes	Yes	Short-range	Isotropic
Solid (crystalline)	Yes	Yes	Long-range	Anisotropic

 Not only atom, ion or molecule positions are repetitious – there are certain symmetry relationships in their arrangement.












 $\mathbf{r} = u\mathbf{a}$ 

One-dimensional lattice with lattice parameter a




Two-dimensional lattice with lattice parameters a, b and  $\gamma$ 






Lattice vectors, lattice parameters and interaxial angles



Lattice vector	а	b	С
Lattice parameter	а	В	С
Interaxial angle	α	β	γ


A lattice is an array of points in space in which the environment of each point is identical




Lattice

Not a lattice

- Unit cell content
  - Coordinates of all atoms
  - Types of atoms
  - Site occupancy
  - Individual displacement parameters



- Usually unit cell has more than one molecule or group of atoms
- They can be represented by symmetry operators




### Symmetry

- Symmetry is a property of a crystal which is used to describe repetitions of a pattern within that crystal.
- Description is done using symmetry operators

$$R \rightarrow R \rightarrow R$$
Translation


m R 9

**Mirror reflection** 



**Rotation** (about axis O)

$$\alpha = 360^{\circ}/n$$
  
where *n* is the *fold* of the axis  $n = 1, 2, 3, 4$  or 6)



**Inversion** 

# Two-dimensional Symmetry Elements




CI Br C == C < F

1

bromochlorofluoroethene

- 1. One-fold axis (no symmetry)
- Я | R (2)


(1)



F H C = C H

m

- 2. Vertical mirror line
- 3. Vertical and horizontal mirror lines
- 4. Two-fold rotation axis
- 5. Three-fold rotation axis





H>c==c<H 2m

2

(4) **(**4)



$$F c = c \begin{cases} F \\ H \end{cases}$$

trans-difluoroethene


trifluoralkylammonia

3

# Two-dimensional Symmetry Elements


- 6. Tree-fold axis + vertical mirror line
- 7. Four-fold axis
- 8. Four-fold axis + mirror lines
- 9. Six-fold axis
- 10. Six-fold axis + mirror lines

10 two-dimensional crystallographic or plane point groups




### The Five Plane $\rho$ 2 Lattices The oblique p-lattice Я | R ρ2mm **⋈**m The rectangular p-lattice c2mm The rectangular *c*-lattice $\rho$ 4mm R The square p-lattice <u>~</u> $\rho$ 6mm R The hexagonal p-lattice

# Two-dimensional Symmetry Elements





### Two-dimensional Symmetry Elements



Lattice type: p for primitive, c for centred

Symmetry elements: *m* for mirror lines, *g* for glide lines, 4 for 4-fold axis etc.






### Bravais Lattices and Crystal Systems


- ◆ In three dimensions: point symmetry elements and translational symmetry elements.
- For point symmetry elements:
  - centers of symmetry
  - mirror planes
  - inversion axes
- For translational symmetry elements:
  - glide planes
  - screw axes


We end up with 230 space groups (was 17 plane groups) distributed among 14 space lattices (was 5 plane lattices) and 32 point group symmetries (instead of 10 plane point symmetries)


### The 14 Space (Bravais) Lattices


- The systematic work was done by Frankenheim in 1835. Proposed 15 space lattices.
- In 1848 Bravais pointed that two of his lattices were identical (unfortunate for Frankenheim).






























Face-centered orthorhombic



Simple


orthorhombic

Rhombohedral




(I)

Monoclinic



monoclinic



**Triclinic** 

a, b, c – unit cell lengths;  $\alpha$ ,  $\beta$ ,  $\gamma$  - angles between them

(P)

# Crystal Symmetry

Centering of the lattice	Lattice points per unit cell	International symbol	Lattice translation(s) due to centering	
Primitive	1	P	None	
Base-centered	2	Α	1/2(b+c)	
Base-centered	2	В	1/2(a+c)	
Base-centered	2	C	1/2(a+b)	
Body-centered	2	I	$1/2(\mathbf{a}+\mathbf{b}+\mathbf{c})$	
Face-centered	4	F	1/2(b+c); $1/2(a+c)$ ; $1/2(a+b)$	
Rhombohedral	3	R	1/3a+2/3b+2/3c; 2/3a+1/3b+1/3c	

# The 14 Space (Bravais) Lattices

4	System Axial len		Bravais lattice	Lattice symbol
	Cubic	Three equal axes at right angles $a = b = c$ , $\alpha = \beta = \gamma = 90^{\circ}$	Simple Body-centered Face-centered	P I F
	Tetragonal	Three axes at right angles, two equal $a = b \neq c$ , $\alpha = \beta = \gamma = 90^{\circ}$	Simple Body-centered	P
	Orthorhombic	Three unequal axes at right angles $a \neq b \neq c$ , $\alpha = \beta = \gamma = 90^{\circ}$	Simple Body-centered Base-centered Face-centered	P I C F
7 crystal systems	Rhombohedral*	Three equal axes, equally inclined $a = b = c$ , $\alpha = \beta = \gamma \neq 90^{\circ}$	Simple	R
	Hexagonal	Two equal coplanar axes at 120°, third axis at right angles $a = b \neq c$ , $\alpha = \beta = 90^{\circ}$ ( $\gamma = 120^{\circ}$ )	Simple	P
	Monoclinic	Three unequal axes, one pair not at right angles $a \neq b \neq c$ , $\alpha = \gamma = 90^{\circ} \neq \beta$	Simple Base-centered	P C
	Triclinic	Three unequal axes, unequally inclined and none at right angles $a \neq b \neq c$ , $(\alpha \neq \beta \neq \gamma \neq 90^{\circ})$	Simple	P
	* Also called trigona	al		


### Crystal Symmetry

- $\diamond$  7 axial systems + 32 point groups  $\rightarrow$  230 unique space groups
- ◆ A 3-D crystal must have one of these 230 arrangements, but the atomic coordinates (i.e. occupied equipoints) may be very different between different crystals

Crystal Class	Non-centrosymmetric Point Group	Centrosymmetric Point Group	Minimum Rotational Symmetry
Triclinic	1	Ī	One 1-fold
Monoclinic	2, m	2/m	One 2-fold
Orthorombic	222, mm2	mmm	Three 2-folds
Tetragonal	4, 422, <del>4</del> , 4mm, <del>4</del> 2m	4/m, 4/mmm	One 4-fold
Trigonal	3, 32, 3 <i>m</i>	$\overline{3},\overline{3}m$	One 3-fold
Hexagonal	6, 622, <del>6</del> , 6 <i>mm</i> , <del>6</del> <i>m</i> 2	6/m, 6/mmm	One 6-fold
Cubic	23, 432, <del>4</del> 3 <i>m</i>	$m\overline{3}, m\overline{3}m$	Four 3-folds


### The Symmetry of Bravais Lattices

Point group symmetry of the cube



- Nine mirror planes
- Three four-fold axes
- Four three-fold axes
- Six two-fold axes


Point group symmetry of the orthorhombic cell



- Three mirror planes
- Three two-fold axes

# Crystal Axes and the Reciprocal Lattice

### Crystal Lattice & Directions



One-dimensional lattice with parameter a

$$\mathbf{r} = u\mathbf{a}$$

$$\mathbf{r} = u\mathbf{a} + v\mathbf{b}$$

Two-dimensional lattice with parameters a and b

### **Lattice Directions**

For the lattice points u, v, w:

$$\mathbf{r} = u\mathbf{a} + v\mathbf{b} + w\mathbf{c}$$


For the points in space u', v', w' that are not lattice points:

$$\mathbf{r} = u'\mathbf{a} + v'\mathbf{b} + w'\mathbf{c}$$

$$= (n + u_1)\mathbf{a} + (p + v_1)\mathbf{b} + (q + w_1)\mathbf{c}$$


$$= (n\mathbf{a} + p\mathbf{b} + q\mathbf{c}) + (u_1\mathbf{a} + v_1\mathbf{b} + w_1\mathbf{c})$$

n, p, q – integers  $u_1$ ,  $v_1$ ,  $w_1$  – fractions



### **Indexing Lattice Directions**

- Direction must pass through the origin
- Coordinates of point P (in fractions of a, b and c) are 1,  $\frac{1}{2}$ , 1  $\Rightarrow$  [212]
- For point Q coordinates are  $\frac{1}{2}$ ,  $\frac{1}{4}$ ,  $\frac{1}{2} \Rightarrow [212]$



[212] – defines direction for OL

For OS – the direction is [110]


$$\mathbf{r}_{102} = 2\mathbf{a} + 1\mathbf{b} + 2\mathbf{c}$$
$$\mathbf{r}_{110} = 1\mathbf{a} + 1\mathbf{b} + 0\mathbf{c}$$

### **Indexing Lattice Directions**


Specific direction  $\Rightarrow [uvw]$ 

Family of directions  $\Rightarrow \langle uvw \rangle$ 

**Example:** 




[3-10]



### **Indexing Lattice Directions**


Directions related by symmetry are called directions of a form.



We have: [111], [-111], [-1-1-1], [11-1], ...




### The Crystallographic Planes



### Definition of the Miller Indices


• Let's draw a plane at  $2 \times a$ ,  $5 \times b$ ,  $2 \times c$ .

	а	b	С
The intercepts	2	5	2
The reciprocals	1/2	1/5	1/2
Multiply by 10	5	2	5
The Miller indices	(525)		




### Definition of the Miller Indices


- For plane A a/2, b/2, and  $1c \Rightarrow 2$ , 2,  $1 \Rightarrow$  plane is (221)
- For plane B 1*a*, 1*b*, and 2*c*  $\Rightarrow$  1, 1, 1/2  $\Rightarrow$  2, 2, 1  $\Rightarrow$  plane is (221)
- For plane C 3*a*/2, 3*b*/2, and 3*c*  $\Rightarrow$  2/3, 2/3, 1/3  $\Rightarrow$  2, 2, 1  $\Rightarrow$  plane is (221)
- For plane D 2*a*, 2*b*, and 4*c*  $\Rightarrow$  1/2, 1/2, 1/4  $\Rightarrow$  2, 2, 1  $\Rightarrow$  plane is (221)



- By the set of crystallographic planes hkl, we mean a set of parallel equidistant planes, one of which passes through the origin, and the next nearest makes intercepts a/h, b/k, and c/l on the three crystallographic axes.
- The integers hkl are usually called the Miller indices.



### Miller Indices



### Miller Indices and Zone Axis Symbols

### Closures for crystallographic indices

[*uvw*] = square brackets designate a direction in the lattice from the origin to a point. Used to collectively include all the faces of a crystals whose intersects (i.e., edges) parallel each other. These are referred to as crystallographic **zones** and they represent a direction in the crystal lattice.


<uv>w> - designate family of directions.


(hkl) = parenthesis designate a crystal face or a family of planes throughout a crystal lattice.

- {hkl} = "squiggly" brackets or braces designate a set of faces that are equivalent by the symmetry of the crystal. The set of face planes results in the **crystal form**. {100} in the isometric class includes (100), (010), (001), (-100), (0-10) and (00-1), while for the triclinic {100} only the (100) is included.
- **d-spacing** is defined as the distance between adjacent planes. When X-rays diffract due to interference amongst a family of similar atomic planes, then each diffraction plane may be reference by it's indices  $d_{hkl}$

### Miller Indices and Zone Axis Symbols

- For cubic crystal:
  - Direction symbols
    - <100> ⇒ [100], [-100], [010], 0 -10], [001], [00 -1]
    - <111> ⇒ [11-1], [-1-11], [1-11], [-11-1], [-111], [1-1-1], [111], [-1-1-1]
    - + <110> ⇒ 12 combinations
  - Miller indices
    - \*  $\{100\} \Rightarrow (100), (-100), (010), (0-10), (001), (00-1)$





### Lattice Plane Spacings

For crystal with orthogonal axes:

$$OA\cos\alpha = ON \rightarrow (a/h)\cos\alpha = d_{hkl} \rightarrow \cos\alpha = (\frac{h}{a})d_{hkl}$$

 $\diamond$  For angles β and γ:

$$\cos \beta = \left(\frac{k}{b}\right) d_{hkl}$$


$$\cos \gamma = \left(\frac{l}{c}\right) d_{hkl}$$

Since for orthogonal axes:

$$\cos^2\alpha + \cos^2\beta + \cos^2\gamma = 1$$

- We write:  $\left(\frac{h}{a}\right)^2 d_{hkl}^2 + \left(\frac{k}{b}\right)^2 d_{hkl}^2 + \left(\frac{l}{c}\right)^2 d_{hkl}^2 = 1$
- For a cubic crystal a = b = c, hence

$$\frac{1}{d_{hkl}^2} = \frac{h^2 + k^2 + l^2}{a^2}$$



Lattice plane – (*hkl*) ON – interplanar spacing

### Lattice Plane Spacings

Cubic:

$$\frac{1}{d^2} = \frac{h^2 + k^2 + l^2}{a^2}$$

Tetragonal:

$$\frac{1}{d^2} = \frac{h^2 + k^2}{a^2} + \frac{l^2}{c^2}$$

Hexagonal:

$$\frac{1}{d^2} = \frac{4}{3} \left( \frac{h^2 + hk + k^2}{a^2} \right) + \frac{l^2}{c^2}$$

Rhombohedral:

$$\frac{1}{d^2} = \frac{(h^2 + k^2 + l^2)\sin^2\alpha + 2(hk + kl + hl)\cos^2\alpha - \cos\alpha}{a^2(1 - 3\cos^2\alpha + 2\cos^3\alpha)}$$

*Orthorhombic:* 
$$\frac{1}{d^2} = \frac{h^2}{a^2} + \frac{k^2}{b^2} + \frac{l^2}{c^2}$$

Monoclinic:

$$\frac{1}{d^2} = \frac{1}{\sin^2 \beta} \left( \frac{h^2}{a^2} + \frac{k^2 \sin^2 \beta}{b^2} + \frac{l^2}{c^2} - \frac{2hl \cos \beta}{ac} \right)$$

Triclinic:

$$\frac{1}{d^2} = \frac{1}{V^2} (S_{11}h^2 + S_{22}k^2 + S_{33}l^2 + 2S_{12}hk + 2S_{23}kl + 2S_{13}hl)$$

V =volume of unit cell

$$S_{11}=b^2c^2\sin^2\alpha,$$

$$S_{22}=a^2c^2\sin^2\beta,$$

$$S_{33}=a^2b^2\sin^2\gamma,$$

$$S_{12} = abc^2(\cos\alpha\cos\beta - \cos\gamma),$$


$$S_{23} = a^2 b c (\cos \beta \cos \gamma - \cos \alpha),$$


$$S_{13} = ab^2c(\cos\gamma\cos\alpha - \cos\beta).$$


### Special Case: Trigonal & Hexagonal Lattices


- (1-10), (100), and (010) are indices different in type but describe crystallographically equivalent lattice planes.
- Introducing the fourth axis U. We have Miller-Bravais indices (hkil).
- $\diamond$  All indices of the planes are of the same form  $-\{10 10\}$ .


$$h + k + i = 0 \Rightarrow i = -(h + k) \Rightarrow \{hk./\}$$





















(001)-


Reciprocal lattice vectors


Reciprocal lattice unit cell



$$\mathbf{c}^* = \mathbf{d}_{001}^*$$
 and  $|\mathbf{c}^*| = 1/d_{001}$ 








- Consider a real space unit cell with real lattice basis vectors a, b and c
- We define a set of reciprocal lattice basis vectors by:

$$\mathbf{a}^* = \frac{1}{V} (\mathbf{b} \times \mathbf{c}) = \frac{\mathbf{b} \times \mathbf{c}}{\mathbf{a} \cdot (\mathbf{b} \times \mathbf{c})}$$

volume of real space unit cell

$$\mathbf{b}^* = \frac{1}{V}(\mathbf{c} \times \mathbf{a})$$
 $\mathbf{c}^* = \frac{1}{V}(\mathbf{a} \times \mathbf{b})$ 

$$\mathbf{c}^* = \frac{1}{V} (\mathbf{a} \times \mathbf{b})$$



Just like we can define a real space lattice in terms of our real space lattice vectors, we can define a reciprocal space lattice in terms of our reciprocal space lattice vectors:

$$\mathbf{r}^* = \mathbf{d}_{hkl}^* = h\mathbf{a}^* + k\mathbf{b}^* + l\mathbf{c}^*$$

The real and reciprocal space lattice vectors form an orthonormal set:


We can define a reciprocal unit cell with volume **V**\*:

$$V^* = \mathbf{a}^* \cdot (\mathbf{b}^* \times \mathbf{c}^*) \qquad V^* \cdot V = 1$$

Now we can write:


$$\mathbf{r}_{uvw} = u\mathbf{a} + v\mathbf{b} + w\mathbf{c}$$

$$\mathbf{d}_{hkl}^* = h\mathbf{a}^* + k\mathbf{b}^* + l\mathbf{c}^*$$




Plan of a cubic I crystal  $\perp z$ -axis

Reciprocal lattice points



Cubic F reciprocal lattice unit cell of a cubic I direct lattice



Cubic *I* reciprocal lattice unit cell of a cubic *F* direct lattice

d-spacing of lattice planes

$$\mathbf{d}_{hkl}^* = h\mathbf{a}^* + k\mathbf{b}^* + l\mathbf{c}^*$$

$$\mathbf{d}_{hkl}^* \cdot \mathbf{d}_{hkl}^* = \frac{1}{d_{hkl}^2} = (h\mathbf{a}^* + k\mathbf{b}^* + l\mathbf{c}^*) \cdot (h\mathbf{a}^* + k\mathbf{b}^* + l\mathbf{c}^*)$$

 $\left(\mathbf{a}^* \cdot \mathbf{a}^* = \frac{1}{a^2}\right)$ 

for orthorombic, tetragonal, cubic:  $\mathbf{a}^* \cdot \mathbf{b}^* = 0$ 

therefore: 
$$\frac{1}{d_{hkl}^2} = h\mathbf{a}^* \cdot h\mathbf{a}^* + k\mathbf{b}^* \cdot k\mathbf{b}^* + l\mathbf{c}^* \cdot l\mathbf{c}^* = \frac{h^2}{a^2} + \frac{k^2}{b^2} + \frac{l^2}{c^2}$$

• Angle  $\rho$  between plane normals  $(h_1k_1l_1)$  and  $(h_2k_2l_2)$ 

the angle between two vectors is  $\cos \rho = \frac{\mathbf{a} \cdot \mathbf{b}}{ab}$ 

therefore: 
$$\cos \rho = \frac{\mathbf{d}_{h_1 k_1 l_1}^* \cdot \mathbf{d}_{h_2 k_2 l_2}^*}{|\mathbf{d}_{h_1 k_1 l_1}^*| |\mathbf{d}_{h_2 k_2 l_2}^*|}$$